

TECHNICAL DATA SHEET

SCC Wax Wrap 80U

BELOW-GROUND

A petroleum-based compound impregnated into a non-woven synthetic carrier, engineered to provide long-term corrosion prevention.



FIELD APPLICATION — BELOW-GRADE PIPELINE

USE

Corrosion prevention for **below-ground** substrates, applied in conjunction with SCC PrimeGuard primer.

PACKAGING

ROLL SIZE	PER CASE	COVERAGE	50% OVERLAP
4" x 9'	24 rolls	72 ft ²	36 ft ²
6" x 9'	16 rolls	72 ft ²	36 ft ²
9" x 18'	6 rolls	81 ft ²	40 ft ²
12" x 18'	4 rolls	72 ft ²	36 ft ²

**Other widths, lengths and 60 mil available.*

ADVANTAGES

- ✓ SP-2, only minimal surface prep required
- ✓ Odorless
- ✓ Wide temp range, wet or dry surfaces
- ✓ No cure time, immediate backfill
- ✓ Meets and complies with AWWA C217 Standard, NACE SP0375-2018
- ✓ Nontoxic, no VOCs
- ✓ No clay fillers
- ✓ Easily conforms to irregular shaped surfaces
- ✓ CP compatible

SPECIFICATIONS

Color	Brown	Application temperature	0°F to 155°F
Thickness	80 mils avg	Operating temperature	-50°F to 155°F
Dielectric strength	296 volts/mil	Drop melt point ASTM D127	179°F
Cathodic disbonding resistance ASTM G-8	Zero disbondment	Cone penetration ASTM D937	6.4
Moisture vapor rate Permeability rate, ASTM E96	0.00024 perms avg.	Flash point ASTM D92	538°F